

LAMIERE NERE

Spessore	Kg per foglio			
	1000	1250	1500	2000
	x 2000	x 2500	x 3000	x 6000
1,5	23,55	36,80	52,99	
2	31,40	49,06	70,65	
2,5	39,25	61,33	88,31	
3	47,10	73,59	105,98	282,60
4	62,80	98,13	141,30	376,80
5	78,50	122,66	176,63	471,00
6	94,20	147,19	211,95	565,20
8	125,60	196,25	282,60	753,60
10	157,00	245,31	353,25	942,00
12	188,40	294,38	423,90	
15	235,50	367,97	529,88	

LAMIERE DECAPATE

Spessore	Kg per foglio		
	1000	1250	1500
	x 2000	x 2500	x 3000
1,5	23,55	36,80	52,99
2	31,40	49,06	70,65
2,5	39,25	61,33	88,31
3	47,10	73,59	105,98
4	62,80	98,13	141,30
5	78,50	122,66	176,63
6	94,20	147,19	211,95
8	125,60	196,25	282,60
10	157,00	245,31	353,25
12	188,40	294,38	423,90

LAMIERE LUCIDE

Spessore	Kg per foglio		
	1000	1250	1500
	x 2000	x 2500	x 3000
0,6	9,42	14,72	21,20
0,8	12,56	19,63	28,26
1	15,70	24,53	35,33
1,2	18,84	29,44	42,39

R.A.R. - Briata

Tel: 0464 421 026 Fax: 431 227 / 480 238


e-mail: INFO@RAR-ROVERETO.IT

LAMIERE ZINCATE

Peso Teorico Kg per foglio

Spessore	1000	1250	1500
	x 2000	x 2500	x 3000
0,5	7,85	12,27	17,66
0,6	9,42	14,72	21,20
0,8	12,56	19,63	28,26
1,0	15,70	24,53	35,33
1,2	18,84	29,44	42,39
1,5	23,55	36,80	52,99
2,0	31,40	49,06	70,65
2,5	39,25	61,33	88,31
3,0	47,10	73,59	105,98

Giallo = Normalmente Disponibile




LAMIERE STRIATE

Peso Teorico Kg per foglio

Spessore	1000	1250	1500
	x 2000	x 2500	x 3000
2,5	49,45	77,27	111,26
3	57,30	89,53	128,93
4	73,00	114,06	164,25
5	88,70	138,59	199,58
6	104,40	163,13	234,90
8	135,80	212,19	305,55
10	167,20	261,25	376,20

Peso Teorico Lamiera Striata = MQ x (Sp. x 7,85 + 5,1)



LAMIERE BUGNATE

Peso Teorico Kg per foglio

Spessore	1000	1250	1500
	x 2000	x 2500	x 3000
2,5	44,25	69,14	99,56
3	52,10	81,41	117,23
4	67,80	105,94	152,55
5	83,50	130,47	187,88
6	99,20	155,00	223,20
8	130,60	204,06	293,85
10	162,00	253,13	364,50

Peso Teorico Lamiera Bugnata = MQ x (Sp. x 7,85 + 2,5)

TEL: 0464 421 026 FAX: 431 227 / 480 238

E-mail: INFO@RAR-ROVERETO.IT

R.A.R. - Briata